



**FTG**  
safety shoes

## TECHNICAL SHEET ART. CHEF WHITE

Class: S2 SRC  
Sizes: 34-48  
Instep: 11  
Weight( $\pm 10\%$ ): 460 gr. (\*)

**Description** low shoe in microfiber water repellent, white color, 100% polyester lining, FTG AIR-WHITE insole extractable and washable, polyurethane outsole white, bending resistant, abrasion resistant, oil resistant, slip resistant, SRC and antistatic

**Suggested sectors of usage** chemical industry/food industry, pharma/hospitals, Cooperative Society

**Care and maintenance** clean periodically the outsole and the upper with non aggressive substances which could compromise the quality, safety and durability of the shoe, do not dry close to direct heat source



Complete shoe	Norm	Description	Unit	FTG result	EN ISO 20345 requirements
<b>Toe cap:</b> Steel toe cap, impact resistant 200 J	5.3.2.3 5.3.2.4	Impact resistance Compression resistance	mm mm	14,0 15,0	$\geq 14$ $\geq 14$
<b>Antistatic footwear:</b> dissipation capacity of the electrostatic charge	6.2.2.2	Electric resistance - Wet (humidity) - Dry	MΩ MΩ	143 528	$\geq 0,1 \text{ M}\Omega$ and $\leq 1000 \text{ M}\Omega$
<b>Capacity of energy absorption in the heel area</b>	6.2.4	Energy absorption in the heel area	J	28	$\geq 20$
<b>Upper:</b> Water-repellent microfiber, white color	5.4.6 5.4.3	Water vapour permeability Coefficient of permeability Tearing strength	mg/cm² h mg/cm² N	6,9 53,7 123	$\geq 0,8$ $\geq 15$ $\geq 60$
<b>Vamp and Quarter lining:</b> 100% honeycomb finished polyester, breathable, abrasion resistant, white color	5.5.3 5.5.1 5.5.2	Water vapour permeability Coefficient of permeability Tearing Strength Abrasion resistance (dry) Abrasion resistance (humidity)	mg/cm² h mg/cm² N cycles cycles	6,8 52,8 73 no rupture no rupture	$\geq 2$ $\geq 20$ $\geq 15$ 25.600 12.800
<b>Insole lining:</b> non woven textile, antistatic	5.7.3	Water Absorption Ability to release water	mg/cm²	108 95%	$\geq 70$ $\geq 80\%$
<b>Sole:</b> white monodensity polyurethane, bending resistant, abrasion resistant, oil resistant, slip resistant SRC, antistatic	5.8.2 5.8.3 5.8.4 5.8.5 6.4.2 5.11	Tearing Strength Abrasion resistance Bendings resistance Hydrolysis Hydrocarbons resistance (volume increase) Slip resistance on ceramic floor with water and detergent Slip resistance on steel floor with glycerine	kN/m mm³ mm mm % flat inclined flat inclined	5,5 98 3,0 2,0 0,2% 0,37 0,28 0,18 0,14	$\geq 5$ $\leq 250$ $\leq 4$ $\leq 6$ $\leq 12\%$ $\geq 0,32$ $\geq 0,28$ $\geq 0,18$ $\geq 0,13$

Azo dye free: no presence of azo dye forbidden by normative 1907/2006/CE Attachment XVII (method UNI EN 14362-1:2012 + 14362:2012 – Textile)

(\*) = Indicative weight that refers to 1/2 pair in size 42