



TECHNICAL SHEET ART. COOK BLACK

Description sabot in black Ecoleather, 100% polyester lining, FTG COMFORT insole extractable and washable, polyurethane outsole black, bending resistant, abrasion resistant, oil resistant, slip resistant, SRC and antistatic



Suggested sectors of usage chemical industry/food industry, pharma/hospitals, Cooperative Society

Care and maintenance clean periodically the outsole and the upper with non aggressive substances which could compromise the quality, safety and durability of the shoe, do not dry close to direct heat source

Class: SB A E WRU FO
SRC
Sizes: 34-48
Instep: 11
Weight(±10%): 460 gr. (*)

Complete shoe

	Norm	Description	Unit	FTG result	EN ISO 20345 requirements
Toe cap: Steel toe cap, impact resistant 200 J	5.3.2.3 5.3.2.4	Impact resistance Compression resistance	mm mm	14,0 15,0	≥ 14 ≥ 14
Antistatic footwear: dissipation capacity of the electrostatic charge	6.2.2.2	Electric resistance - Wet (humidity) - Dry	MΩ MΩ	144 517	≥ 0,1 MΩ and ≤ 1000 MΩ
Capacity of energy absorption in the heel area	6.2.4	Energy absorption in the heel area	J	27	≥ 20
Upper: Ecoleather, black color	5.4.6 5.4.3	Water vapour permeability Coefficient of permeability Tearing strength	mg/cm² h mg/cm² N	7,1 54,0 128	≥ 0,8 ≥ 15 ≥ 60
Vamp and Quarter lining: 100% honeycomb finished polyester, breathable, abrasion resistant, black color	5.5.3 5.5.1 5.5.2	Water vapour permeability Coefficient of permeability Tearing Strength Abrasion resistance (dry) Abrasion resistance (humidity)	mg/cm² h mg/cm² N cycles cycles	6,8 52,8 73 no rupture no rupture	≥ 2 ≥ 20 ≥ 15 25.600 12.800
Insole lining: non woven textile, antistatic	5.7.3	Water Absorption Ability to release water	mg/cm²	108 95%	≥ 70 ≥ 80%
Sole: black monodensity polyurethane, bending resistant, abrasion resistant, oil resistant, slip resistant SRC, antistatic	5.8.2 5.8.3 5.8.4 5.8.5 6.4.2 5.11	Tearing Strength Abrasion resistance Bendings resistance Hydrolysis Hydrocarbons resistance (volume increase) Slip resistance on ceramic floor with water and detergent Slip resistance on steel floor with glycerine	kn/m mm³ mm mm % flat inclined flat inclined	5,5 98 3,0 2,0 0,2% 0,37 0,28 0,18 0,14	≥ 5 ≤ 250 ≤ 4 ≤ 6 ≤ 12% ≥ 0,32 ≥ 0,28 ≥ 0,18 ≥ 0,13

Azo dye free: no presence of azo dye forbidden by normative 1907/2006/CE Attachment XVII (method UNI EN 14362-1:2012 + 14362:2012 – Textile)

(*) = Indicative weight that refers to 1/2 pair in size 42